

UNIVERSAL FLOOR MASTER

Chlorinated Rubber Based Paint



DESCRIPTION:

A premium quality floor coating for interior & exterior applications.

This products exhibits outstanding weather, alkali, chemical, solvent, UV and abrasion resistance.

RECOMMENDED USES:

Areas exposed to chemicals and highly corrosive environments such as manufacturing facilities as well as exterior high-traffic areas such as sports facilities and parking lots.

PRODUCT APPEARANCE	: Liquid
PACKAGE VISCOSITY	: 70-75 kus
DRY FILM THICKNESS	:
DRY SET TO TOUCH	: 2 hours
DRY HARD	: 24 hours
COATING INTERVAL	: 4 hours
THINNING	: CRB Reducer
APPLICATION	: brush, roller, spray
COVERAGE	: 20-25 m ² /4L depending on surface porosity & texture
CLEAN-UP	: CRB Reducer
PACKAGING SIZE	: 1, 4 liters
AVAILABLE COLORS	: Winter White PRO-700 Battleship Gray PRO-701 Smoke Gray PRO-701A Pine Green PRO-702 Safety Yellow PRO-704 Cardinal Red PRO-705 Safety Orange PRO-706 Riviera PRO-709 Blue Bay PRO-703 Ocean Blue PRO-703A Granite PRO-710 Onyx PRO-711 Pale Pewter PRO-707 Dune Beige PRO-708

Color can be customized to client's needs. Please call us for details.

FINISH : Gloss

SURFACE PREPARATION:

Masonry

New or unpainted surface

Remove dirt, dust, grit, loose mortar, oil, grease and other contaminants. New concrete must be cured at least 28 days before paint application. Please follow manufacturer's recommendation to check use litmus paper test.

Old or previously painted surface

Remove all loose, peeling, chalking or blistering paint, dirt, dust, grease, oil and other contaminants. Treat mold or fungus infestation with bleaching solution (1 part bleach and 3 parts water).

Metal

New or unpainted surface

Ensure that the metal surface is free from oil, grease, rust, and other surface contaminants. Remove thick rust by sand blasting and thin rust by wire brushing, sanding or scraping. Dust the surface and wipe surface clean prior to priming with metal primer red oxide.

Old or previously painted surface

Remove all loose, peeling, paint, rust, dirt, dust, grease, oil and other contaminants by wire brushing or scraping. Wipe surface clean and priming with metal primer red oxide.

UNIVERSAL FLOOR MASTER

Chlorinated Rubber Based Paint



APPLICATION:

Do not thin. Inter-mix all cans of same color to ensure color uniformity and consistency. Always stir paint before and occasionally during application. Apply only when temperature is from 10° – 35°C. Do not paint in rain or rain imminent weather. For best results always use high quality roller and brush.

PAINTING DIRECTIONS: For best results use:

Masonry

1st coat: Universal Floor Master Deep Penetrating Sealer PRO-730

To remedy surface imperfections:

Putty: Otto Polybond Polyester Body Filler OTTO-500

2nd coat: Universal Floor Master Epoxy Floor Primer PRO-XXX.

Allow 8 hours drying time then sand.

3rd coat: Universal Floor Master Chlorinated Rubber Based Paint of desired color, with light sanding in between coats

Metal

1st coat: Universal Floor Master Epoxy Primer PRO-800.

2nd-3rd coat: Universal Floor Master Chlorinated Rubber Based Paint of desired color, with light sanding in between coats

Apply more coats if higher hiding is desired.