

UNIVERSAL FLOOR MASTER

Self-Leveling Epoxy Topcoat



DESCRIPTION:

A premium high grade solvent less epoxy paint formulated for heavy duty floor coating.

It features excellent leveling properties, high chemical, abrasion and impact resistance. Moreover, it is also formulated to have excellent color retention and high gloss.

RECOMMENDED USES:

Leveling uneven or pockmarked concrete surfaces.

PRODUCT APPEARANCE	: Liquid		
PACKAGE VISCOSITY	: Viscous liquid		
DRY FILM THICKNESS	:		
DRY SET TO TOUCH	: 4 hours		
DRY HARD	: 48 hours for pedestrian traffic, 3-4 days vehicular traffic		
THINNING	: Do not reduce, Apply at package consistency		
MIXING RATIO	: 2 Parts Topcoat 1 Part SL Catalyst		
INDUCTION TIME	:		
APPLICATION	: by trowel, brush, roller		
COVERAGE	: For thickness of:	0.5 – 0.7mm	= 8 - 10 m ² /4L
		2mm	= 3 - 4 m ² /4L
		3mm	= 2 - 3 m ² /4L
CLEAN-UP	: Epoxy Reducer		
PACKAGING SIZE	: 4 Liters		
AVAILABLE COLORS	: Black	PRO-772	
	Winter White	PRO-771	Battleship Gray PRO-774
	Smoke Gray	PRO-774A	Pine Green PRO-775
	Safety Yellow	PRO-776	Cardinal Red PRO-777
	Safety Orange	PRO-778	Riviera PRO-786
	Blue Bay	PRO-773	Ocean Blue PRO-773A
	Granite	PRO-787	Onyx PRO-778
	Pale Pewter	PRO-779	Dune Beige PRO-785
	<i>Color can be customized. Please call us for details.</i>		
FINISH	: High gloss finish		

SURFACE PREPARATION:

New or unpainted surface

Remove dirt, dust, grit, loose mortar, oil, grease and other contaminants. New concrete must be cured at least 28 days before paint application. Please follow manufacturer's recommendation to check use litmus paper test.

Old or previously painted surface

Remove all loose, peeling, chalking or blistering paint, dirt, dust, grease, oil and other contaminants. Treat mold or fungus infestation with bleaching solution (1 part bleach and 3 parts water).

UNIVERSAL FLOOR MASTER

Self-Leveling Epoxy Topcoat



APPLICATION:

Do not thin. Inter-mix all cans of same color to ensure color uniformity and consistency. Always stir paint before and occasionally during application. Apply only when temperature is from 10° – 35°C. Do not paint in rain or rain imminent weather. For best results always use high quality roller and brush.

PAINTING DIRECTIONS: For best results use:

- 1st coat: Universal Floor Master Solvent-Less/Self-Leveling Epoxy Primer PRO-770.
Allow 8 hours drying time.
- 2nd coat: Universal Floor Master Solvent-Less/Self-Leveling Topcoat PRO-XXX of
desired color. Allow 48 hours drying time for pedestrian traffic and 3-4 days
maximum cure for vehicular traffic.

Apply more coats if higher hiding is desired.